



F1-0001V

FEATURES

- Very High Clarity
- Good mechanical shear stability
- Low bleed and evaporation
- Excellent adhesion

APPLICATIONS

Reduce internal reflection and refraction in optical instruments

- Optical cameras
- Gamma cameras
- Scintillators
- Fiber Optics

FIS Matching Gel helps to reduce optical loss within fiber optic mechanical splices and connectors, apply optical couplant at the interface of the two mated fibers. This minimizes loss by reducing the difference in the index of refraction between the mated fibers.

SPECIFICATIONS

Appearance	Clear, Transparent
Size	0.40 oz
Penetration (Worked 60X), ASTM D217	317
Bleed (100°C/24 Hours)	0.18%
Evaporation (100°C/24 Hours)	0.36
Specific Gravity	1.06
Index of Refraction	1.463
Light Transmittance, %	
400nm (1) Nanometers	96%
425nm	98%
450nm	98%
500nm	98%

Restrictions: Light transmission is adversely affected by temperature. Maximum clarity with F1-0001V is between 65 and 80°F (18 to 27°C). Do not use with applications involving highly oxidative chemicals such as pure oxygen, nitrates, peroxides or chlorine; strong mineral acids such as sulfuric, hydrochloric and nitric; strongly alkaline materials such as sodium or potassium hydroxide. Do not use in surface to be painted.

Special Storage Instructions: F1-0001V may be stored at 70°F (21°C) or below for periods up to six (6) months. Elevated storage temperatures or longer periods of storage will result in a slow softening of the compound. Storage at temperatures below 40°F (4°C) is recommended for extended storage. Although the compound may soften, other properties are unaffected and the compound may be used for its intended purpose.