


Electro-Optic DAST Crystals

DAST: 4'-dimethylamino-N-methyl-4-stilbazolium tosylate



Properties

- high quality crystals
- cut and polished for various applications
- large nonlinear optical susceptibilities ($d_{11} > 1000\text{pm/V}$)
- large electro-optic coefficients ($r_{11}=92 \text{ pm/V}$)

Applications


- efficient THz generation and detection
- fast electro-optic modulation
- optical parametric generation
- efficient frequency doubling of 1.55 μm radiation

Physical Properties


melting point	256 °C
refractive indices	$n_1(720 \text{ nm}) = 2.519$, $n_2(720 \text{ nm}) = 1.720$, $n_3(720 \text{ nm}) = 1.635$
nonlinear optical coefficients*	$d_{11}(1318 \text{ nm}) = 1010 \text{ pm/V}$ $d_{11}(1542 \text{ nm}) = 290 \text{ pm/V}$, $d_{26}(1542 \text{ nm}) = 39 \text{ pm/V}$
electro optic coefficients	$r_{11}(720 \text{ nm}) = 92 \text{ pm/V}$ $r_{11}(1313 \text{ nm}) = 53 \text{ pm/V}$ $r_{11}(1535 \text{ nm}) = 47 \text{ pm/V}$
dielectric constants	$\epsilon_1(3\text{kHz}) = 5.2$, $\epsilon_2(3\text{kHz}) = 4.1$, $\epsilon_3(3\text{kHz}) = 3.0$

*based on $d_{11} = 0.29 \text{ pm/V}$ of α -quartz

Absorption Spectrum



THz Generation



- 1) "Photonic applications with the organic nonlinear optical crystal DAST"; M. Jazbinsek, L. Mutter, P. Gunter. IEEE Journal of selected topics in Quantum Electronics 14 (5), 1298-1311 (2008).
- 2) "Generation of terahertz pulses through optical rectification in organic DAST crystals: Theory and experiment"; A. Schneider, M. Neis, M. Stillhart, B. Ruiz, R. U. A. Khan, and P. Günter, J. Opt. Soc. Am. B 23 (9), 1822-1835 (2006).
- 3) "High Efficiency Generation and Detection of Terahertz Pulses Using Laser Pulses at Telecommunication Wavelengths"; A. Schneider, M. Stillhart and P. Günter, Optics Express 14 (12), 5376-5384 (2006).

Rainbow Photonics AG

Farbhofstrasse 21
CH-8048 Zürich

Phone: +41 44 419 05 05
Fax: +41 44 419 05 06
E-mail: info@rainbowphotonics.com
Web: www.rainbowphotonics.com

